

Precision Steel

# precidur<sup>®</sup> HSM 460 / S460MC

Product information for hot-rolled precision strip made in Hohenlimburg



thyssenkrupp

Version 9/21

## Microalloyed fine grain structural steel

Microalloyed fine grain structural steels are produced with low carbon equivalents in accordance with DIN EN 10149.

Hot-rolled fine grain structural steels are particularly suitable for direct processing with extended cold formability requirements. HSM steels (Hohenlimburg special structural steels, microalloyed) are suitable for bending and roll forming with tight radii and – with restrictions in the case of high-strength grades – deep drawing and stretch forming.

## precidur<sup>®</sup>

- is used in virtually all industry sectors.
- offers close thickness tolerances similar to cold-rolled strip, optimum surface finishes and consistent material properties over the entire strip length and width.
- is characterized by its symmetrical strip profiles and mill edges.
- is the sum of all the experience we have gained in more than 100 years of manufacturing and processing steel.

---

## Contents

Brief portrait  
Technical features  
Chemical composition  
Mechanical properties  
General thickness tolerances  
Delivery options  
Application examples

---

## Technical features

Microalloyed fine grain structural steel

Material number:	1.0982
Material name:	S460MC / H460LA
Proprietary brand:	precidur® HSM 460
Delivery specification:	DIN EN 10149-2 / VDA 239-100
Application:	Steels with very good forming, fine blanking and welding properties

### Chemical composition

Ladle analysis mass percentages	C [%]	Si [%]	Mn [%]	P [%]	S [%]	Al [%]	Nb [%]	V [%]	Ti [%]
min.	-	-	-	-	-	0.015	-	-	-
max.	0.10	0.30	1.60	0.020	0.010	0.070	0.09	0.10	0.10

Further special analyses available

### Mechanical properties

Longitudinal to rolling direction	Yield strength $R_{eH}$ [MPa]	Tensile strength $R_m$ [MPa]	Elongation $A_5$ [%]	$A_{80}$ [%]
precidur® HSM 460	min. 460	520 - 620	min. 20	min. 17

### Possible delivery options

Options	Mill edge (NK) Cut edge (GK)	pickled	unpickled	slit	trimmed	Cut to length
precidur® HSM 460	NK or GK	✓	or ✓	✓	✓	✓

### General thickness tolerances

Strip thickness [mm]	1.5 – 2.54	2.55 – 4.03	4.04 – 6.03	6.04 – 8.03	8.04 – 9.03	9.04 – 11.03	11.04 – 14.03	14.04 – 16.00
Standard tolerances [mm]	± 0.04	± 0.04	± 0.05	± 0.055	± 0.06	± 0.07	± 0.08	± 0.10
Special tolerances [mm]	± 0.03	± 0.035	± 0.04	± 0.045	± 0.05	± 0.055	± 0.06	± 0.07

### General delivery options

Coil inner diameter:	standard 508 mm / optional 610 mm
Coil outer diameter:	max. 1,890 mm
Coil weight:	max. 20.5 kg/mm strip width
Strip width*:	max. 720 mm
Strip thickness*:	1.5 – 16 mm

\* May be subjected to restrictions.

## Application examples for microalloyed fine grain structural steel



Special mill grades feature unique thyssenkrupp properties. Other terms and conditions of supply not specified here will be based on the applicable specifications. The specifications used will be those valid on the date of publication of this product information.

### General information:

All statements as to the properties or utilization of material and products are for the purpose of description only. Guarantees in respect of the existence of certain properties or utilization are only valid if agreed in writing. Subject to technical changes. Reprints, in whole or in part, only with the permission of thyssenkrupp Hohenlimburg GmbH. The latest version of this product information can be found at: <https://www.thyssenkrupp-steel.com/en/publications/>

Please contact our sales/technical customer support team for detailed information.

thyssenkrupp Hohenlimburg GmbH, Oeger Str. 120, 58119 Hagen  
T: +49 2334 91 2555  
[www.thyssenkrupp-steel.com](http://www.thyssenkrupp-steel.com), [info.precisionsteel@thyssenkrupp.com](mailto:info.precisionsteel@thyssenkrupp.com)